

PHYSICAL AND MECHANICAL BEHAVIOURS OF PINEAPPLE LEAF FIBRE
REINFORCED THERMOPLASTICS CORN STARCH BIOPOLYMER
COMPOSITES

NAZRI HUZAIMI BIN ZAKARIA

A thesis submitted in
fulfilment of the requirement for the award of the
Doctor of Philosophy.

Faculty of Mechanical and Manufacturing Engineering
Universiti Tun Hussein Onn Malaysia

AUGUST 2020

To my precious Allah S.W.T,
Who gives me new life, hope and purpose of life

To my beloved father and mother
Zakaria Bin Hj. Mohammad & Salasiah Binti Shafie
Al-Fatihah

To my supervisor and co-supervisor,
Prof Madya Dr Mohd Zamani Bin Ngali,
Prof Madya Dr Mohd Zulkefli Bin Selamat
For their continuous advice, support and patience while finishing this thesis

To my beloved wife and sons,
Nur Eirna Binti Jamaluddin,
Aryan Danish, Aryan Daniyal & Aryan Daiyan
For understanding and encouragement

And to all my friends,
For their encouragement, cooperation and motivation in completing this thesis

ACKNOWLEDGEMENTS

In Allah name, Most Gracious, Most Merciful

The highest gratitude to Allah S.W.T for the strength, resilience and wisdom to complete this thesis. The completion of this thesis would not have taken place without His blessing and guidance. My deepest appreciation goes to my caring supervisor, Associate Professor Dr Mohd. Zamani Bin Ngali for his tremendous support and supervision during my thesis. Under his direction, I was motivated to explore the world of science and writing. After that, I would like to take this opportunity to express my co-supervisors, Associate Professor Dr Mohd Zulkefli Bin Selamat (UTeM) for his support and coaching.

I would like to express my sincere appreciation to Universiti Teknikal Malaysia Melaka (UTeM) and the Malaysian Ministry of Higher Education for supporting me with the scholarship award to proceed with this study

I thank especially for her constant support and devotion to my beloved wife (Nur Eirna Binti Jamaluddin) during my study. To all my beloved family of encouragement and constant prayer for my success in this life and the afterlife. Special thanks to my sons (Aryan Danish, Aryan Daniyal and Aryan Daiyan) for providing me with a cheerful feeling during my period of the study.

I am grateful to all employees of the Faculty of Mechanical and Manufacturing Engineering (UTHM), Faculty of Mechanical Engineering and Faculty of Mechanical and Manufacturing Engineering Technology (UTeM) for their assistance and guidance. Last but not least, I want to thank all my friends for the sharing of knowledge and help to complete this work successfully.

Thank you, love all of you!!!

ABSTRACT

Recently, the desire to develop environmentally friendly products is growing due to the accumulating of non-biodegradable waste, mainly the disposable product. Starch is one of the potential materials due to the easy availability, low cost, renewability and biodegradability. However, the natural behaviours associated with corn starch (CS) have demonstrated poor mechanical behaviours. Therefore, the modification of CS with the glycerol was applied to form thermoplastics corn starch (TPCS). Hence, characterizations of the TPCS were investigated and the best result was obtained from a mixture of 70 wt.% CS and 30 wt.% glycerol. Meanwhile, pineapple leaf fibre (PALF) is a versatile plant which can be considered a renewable source for composite development. Then, the modification procedure to enhance the behaviours of TPCS reinforced by PALF was employed by using several method; (1) preparation by using multi layers and single layer (2) reinforcement with different lengths of PALF, and (3) treatment with sodium hydroxide (NaOH). PALF reinforcement at the weight ratio of 20:80, 30:70, 40:60, 50:50, and 60:40 was prepared with TPCS. Consequently, the findings showed that the mechanical behaviours of the treated PALF/TPCS bio-composite were improving via single layer. The tensile strength at low PALF loadings produced low values but when reached 40 to 50 wt.%, the tensile strength achieved the highest results. In terms of physical analysis, the preparation of treated PALF/TPCS bio-composite by single layer had a significant impact on moisture absorption and water absorption characteristics. In addition, the tests such as soil burial and water solubility were also affected by the fibre loading. Next, the PALF length affected the physical and mechanical behaviours of PALF/TPCS bio-composite. PALF with a length of 10 mm showed better characteristics than the length of 2 mm and 30 mm. In conclusion, the TPCS/PALF bio-composites are potential materials for biodegradable products such as non-load bearing applications.

ABSTRAK

Kebelakangan ini, keperluan untuk membangunkan produk mesra alam semakin meningkat disebabkan oleh sisa terkumpul yang tidak terbiodegradasi, terutamanya produk pakai buang. Kanji adalah bahan yang berpotensi kerana mudah diperolehi, kos yang rendah, boleh diperbaharui dan mesra alam. Walau bagaimanapun, sifat semulajadi yang berkaitan dengan kanji jagung (CS) adalah mempunyai sifat mekanikal yang lemah. Oleh itu, pengubahsuaian terhadap CS dengan gliserol telah dijalankan untuk membentuk kanji jagung termoplastik (TPCS). Oleh itu, pencirian TPCS telah disiasat dan hasil yang terbaik diperolehi daripada campuran 70 wt.% kanji jagung dan 30 wt.% gliserol. Sementara itu, serat daun nanas (PALF) adalah tumbuhan serba boleh yang boleh dianggap sebagai sumber yang boleh diperbaharui untuk di buat komposit. Kemudian, prosedur pengubahsuaian untuk meningkatkan sifat-sifat TPCS yang diperkuat oleh PALF dengan menggunakan beberapa kaedah; (1) penyediaan dengan menggunakan pelbagai lapisan dan lapisan tunggal (2) pengukuhan dengan panjang PALF yang berlainan dan (3) rawatan dengan natrium hidroksida (NaOH). Penguatan PALF pada nisbah berat 20:80, 30:70, 40:60, 50:50, dan 60:40 disediakan bersama dengan TPCS. Hasilnya, penemuan menunjukkan sifat mekanikal bio-komposit PALF/TPCS yang dirawat meningkat melalui lapisan tunggal. Kekuatan tegangan pada beban PALF rendah menghasilkan nilai yang rendah tetapi apabila mencapai 40 hingga 50 wt.%, kekuatan tegangan mencapai hasil yang tertinggi. Dari segi analisis fizikal, penyediaan bio-komposit PALF/TPCS dengan lapisan tunggal mempunyai kesan yang signifikan terhadap sifat penyerapan kelembapan dan penyerapan air. Di samping itu, ujian seperti penanaman di dalam tanah dan kelarutan di dalam air juga dipengaruhi oleh berat serat. Seterusnya, panjang PALF menjejaskan sifat fizikal dan mekanikal bio-komposit PALF/TPCS. PALF dengan panjang 10 mm menunjukkan sifat-sifat yang lebih baik daripada panjang 2 mm dan 30 mm. Sebagai kesimpulan, bio-komposit PALF/TPCS adalah bahan yang berpotensi untuk produk biodegradasi seperti aplikasi tanpa beban.

CONTENTS

TITLE	i
DECLARATION	ii
DEDICATION	iii
ACKNOWLEDGEMENTS	iv
ABSTRACT	v
ABSTRAK	vi
LIST OF TABLES	x
LIST OF FIGURES	xi
LIST OF SYMBOLS AND ABBREVIATIONS	xvi
LIST OF APPENDICES	xvii
CHAPTER 1 INTRODUCTION	1
1.1 Background study	1
1.2 Problem statements	2
1.3 Objectives	4
1.4 Scope of the study	4
1.5 Significance of the study	6
CHAPTER 2 LITERATURE REVIEW	7
2.1 Introduction	7
2.2 Composites	8
2.3 Bio-composites	13
2.4 Natural fibres	15
2.4.1 Pineapple leaf fibre (PALF)	17
2.4.2 Fibre surface treatment	20
2.4.3 PALF based composites	27
2.5 Starch	31
2.5.1 Polymerization of thermoplastics starch	33
2.5.2 Biodegradable behaviours of TPS	34

2.5.3	Thermoplastic corn starch (TPCS) based composites	36
2.5.4	Applications of thermoplastic starch	39
2.6	Preparation method	40
2.6.1	Fibre length	41
2.6.2	Fibre orientation	43
2.6.3	Fibre loading	46
2.7	Summary	48
CHAPTER 3 METHODOLOGY		49
3.1	Experimental overview	49
3.2	Materials	52
3.2.1	Corn starch	52
3.2.2	Glycerol	52
3.2.3	Pineapple leaf fibre	53
3.2.4	Sodium hydroxide (NaOH) pellets	54
3.3	Experimental procedures	54
3.3.1	Preparation of thermoplastics corn starch (TPCS)	54
3.3.2	Determination of the ideal compression moulding parameter for CS/glycerol	57
3.3.3	Preparation of PALF surface treatment	57
3.3.4	Cutting proses for PALF	58
3.3.5	Preparation of PALF/TPCS composites through multi layers (lamine)	59
3.3.6	Preparation of PALF/TPCS composites through single layer	61
3.4	Characterization of samples	63
3.4.1	Mechanical testing	63
3.4.2	Physical testing	66
CHAPTER 4 RESULTS AND DISCUSSION		70
4.1	Preparation of thermoplastics corn starch (TPCS)	70
4.1.1	Determination of compression moulding parameter for virgin TPCS	71

4.1.2	Determination of the mechanical and physical behaviour of virgin TPCS	72
4.2	Preparation of pineapple leaf fibre (PALF)	78
4.2.1	Fibre surface treatment	78
4.3	Untreated PALF/TPCS composites for different fibre types	80
4.4	Untreated PALF/TPCS composites for 2 mm and 10 mm of length	92
4.5	Treated PALF/TPCS composites for 10 mm length	109
4.6	Treated PALF/TPCS composites for 10 mm and 30 mm of length	126
CHAPTER 5 CONCLUSIONS AND RECOMMENDATIONS		141
5.1	Conclusions	141
5.2	Recommendations	144
REFERENCES		145
APPENDICES		171
LIST OF PUBLICATIONS		175



PTTHA UTHM
PERPUSTAKAAN TUNKU TUN AMINAH

LIST OF TABLES

2.1	Chemical composition of common lignocellulosic fibre	16
2.2	Mechanical properties of important lignocellulosic fibre	16
2.3	Chemicals composition of PALF	19
2.4	Physical and mechanical strength of PALF	20
2.5	Properties of PALF from Malaysia cultivar	20
2.6	Effect of surface treatments of PALF reinforced polymer composites from literature	25
2.7	PALF reinforced biodegradable polymer composites	29
2.8	Thermoplastic corn starch composites	38
2.9	The effect of different fibre length for thermoplastics composites	43
2.10	Various proportions of fibres in the hybrid composite	47
3.1	Material specification of glycerol	53
3.2	Composition of CS/glycerol	56
3.3	Parameters outline for CS/glycerol	57
3.4	Composition of PALF/TPCS for each layer (wt.%)	61
3.5	Parameters outline for PALF/TPCS	61
3.6	Composition of PALF/TPCS (wt.%)	62
4.1	Three best of the samples	72
4.2	Hardness test for the mixture of CS and glycerol	74
4.3	Density properties of corn starch/glycerol (TPCS)	75
4.4	Moisture content properties of corn starch/glycerol (TPCS)	76
4.5	Tensile strength of PALF/biodegradable reinforced polymer composites	128

LIST OF FIGURES

2.1	Building using straw and mud	7
2.2	Classification of natural and synthetics fibres	9
2.3	Overview of the polymer matrix composite (PMCs)	10
2.4	Classification of composite materials (a) Fibre, (b) Particulate, (c) Flake, (d) Filled, (e) Laminar	11
2.5	Types of fibre reinforcement composites (a) Continuous, (b) Woven, (c) Chopped, (d) Hybrid	11
2.6	Classification of macro structural composite	12
2.7	Broad classification bio-composites	14
2.8	Proses of production pineapple leaf fibre (PALF)	18
2.9	Typical structure (a) untreated (b) alkalized cellulosic fibre	22
2.10	Cellulose microfibril structure model	22
2.11	SEM micrographs of longitudinal views of (a) untreated hemp fibre and (b) 6% NaOH treated hemp fibre	24
2.12	SEM micrographs of longitudinal views of (a) untreated kenaf fibre and (b) 6% NaOH treated kenaf fibre	24
2.13	Scanning electron micrographs of starch granules from native corn starch	31
2.14	Schematic diagram of (a) amylose and (b) amylopectin with a branch point	32
2.15	Weight loss of TPS/eggshell and TPS/CaCo ₃ after soil burial for 15 days	35
2.16	Shape of fibres in composites (a) short (b) long (c) continues	41
2.17	Example of the orientation of fibre in composite (a) discontinuous and randomly oriented (b) discontinuous and aligned (c) continuous and aligned (d) fabric or woven or bidirectional	43

2.18	Example of laminate composites (a) continuous (b) discontinuous and random (c) discontinuous and aligned	44
2.19	Fibre orientations for PALF reinforced bisphenol composite	44
2.20	Geometry of unidirectional composite (a) Longitudinal (Iso-strain) (b) Transverse (Iso-stress)	45
3.1	Flowchart of the process	51
3.2	Corn starch (Powder)	52
3.3	Glycerol	52
3.4	Pineapple leaf fibre (PALF)	53
3.5	Sodium hydroxide (NaOH)	54
3.6	Motorise hydraulic moulding test press	55
3.7	Mild steel mould	55
3.8	Dimension of mould	55
3.9	Sample for TPCS	56
3.10	Flow of alkaline treatment process; a) Soaking in NaOH b) Drying process c) Treated fibres d) Fibre after grooming	58
3.11	Cutting box	59
3.12	Different length of PLF (a) 2 mm (b) 10 mm (c) 30 mm (approximately)	59
3.13	Hydraulic press machine	60
3.14	Multi Layers (laminated) composites drawing	60
3.15	Actual sample for multi layers (laminated) composite	60
3.16	Ball mill machine	62
3.17	Actual sample for single layer composite	63
3.18	Instron universal testing machine model (INSTRON 5969)	64
3.19	Pendulum impact tester model Vector	65
3.20	The electronic densimeter (MD-300s)	67
3.21	Humidity chamber (GOTECH GT-7005)	68
3.22	Scanning electron microscope (SEM)	69
4.1	Incompletely melt of TPCS	71
4.2	Tensile strength of corn starch blended with glycerol	73
4.3	Water absorption for corn starch/glycerol (TPCS)	77
4.4	SEM micrograph of corn starch blended with different loadings of glycerol (a) 30 wt.% (b) 35 wt.% (c) 40 wt.%	78

4.5	PALF (a) Untreated PALF (b) Treated PALF	79
4.6	SEM micrographs untreated PALF	79
4.7	SEM micrographs treated PALF	80
4.8	The comparison of tensile strength against untreated PALF/TPCS loading in different fibre types for 2 mm length	82
4.9	The comparison of flexural strength against untreated PALF/TPCS loading for different fibre types for 2 mm length	82
4.10	The comparison of impact tests for different fibre types for 2 mm length	84
4.11	The comparison of density testing for different fibre types for 2 mm length	85
4.12	The comparison of moisture content for different fibre types for 2 mm length	86
4.13	The moisture absorption for multi layers and a single layer for 2 mm length	87
4.14	The water absorption for multi layers and a single layer in 0.5 hours and 2 hours for 2 mm length	88
4.15	The comparison of water solubility for different fibre types for 2 mm length	89
4.16	The comparison of soil burial in 2 and 4 weeks for different fibre types for 2 mm length	90
4.17	SEM of the tensile failure surface of TPCS blended with the different fibre content of untreated PALF for multi layers in 2 mm length (a) 20 wt.% (b) 40 wt.% (c) 60 wt.%	91
4.18	SEM of the tensile failure surface of TPCS blended with different fibre content of untreated PALF for single layer in 2 mm length (a) 20 wt.% (b) 40 wt.% (c) 60 wt.%	92
4.19	The tensile strength and modulus against untreated PALF / TPCS loading for a single layer of 2 mm and 10 mm lengths	94
4.20	The flexural strength and modulus against untreated PALF/ TPCS loading for a single layer for 2 mm and 10 mm lengths	96
4.21	The comparison of impact tests for 2 mm and 10 mm lengths	97
4.22	The density testing for a single layer for 2 mm and 10 mm lengths	98

4.23	The moisture content for a single layer for 2 mm and 10 mm lengths	100
4.24	The moisture absorption for a single layer for 2 mm and 10 mm lengths	101
4.25	The water absorption for a single layer in 0.5 hours and 2 hours for 2 mm and 10 mm lengths	103
4.26	The water solubility for a single layer for 2 mm and 10 mm lengths	104
4.27	The soil burial for a single layer in 2 weeks and 4 weeks for 2 mm and 10 mm lengths	106
4.28	SEM of the tensile failure surface of TPCS blended with the different fibre content of untreated PALF for a single layer in 2 mm of length (a) 20 wt.% (b) 40 wt.% (c) 60 wt.%	108
4.29	SEM of the tensile failure surface of TPCS blended with different fibre content of untreated PALF for a single layer in 10 mm of length (a) 20 wt.% (b) 40 wt.% (c) 60 wt.%	108
4.30	The comparison of tensile strength against PALF/TPCS loading for untreated and treated PALF	110
4.31	The comparison of flexural strength against PALF/TPCS loading for untreated and treated PALF	112
4.32	The comparison of impact tests for untreated and treated PALF	113
4.33	The comparison of density testing for untreated and treated PALF	115
4.34	The comparison of moisture content for untreated and treated PALF	116
4.35	The moisture absorption for untreated and treated PALF	118
4.36	The water absorption in 0.5 hours and 2 hours for untreated and treated PALF	120
4.37	The comparison of water solubility for untreated and treated PALF	122
4.38	The comparison of soil burial in 2 and 4 weeks for untreated and treated PALF	123

4.39	SEM of the tensile failure surface of TPCS blended with the different fibre content of untreated PALF for a single layer in 10 mm length (a) 20 wt.% (b) 40 wt.% (c) 60 wt.%	125
4.40	SEM of the tensile failure surface of TPCS blended with different fibre content of treated PALF for a single layer in 10 mm length (a) 20 wt.% (b) 50 wt.% (c) 60 wt.%	126
4.41	The comparison of tensile strength against treated PALF/TPCS loading for different lengths	128
4.42	The comparison of flexural strength against treated PALF/TPCS loading for different length	129
4.43	The comparison of impact tests for different lengths	130
4.44	The comparison of density testing for different length	131
4.45	The comparison of moisture content for different length	132
4.46	The moisture absorption for different length	134
4.47	The water absorption in 0.5 hours and 2 hours for different lengths	135
4.48	The comparison of water solubility for different length	137
4.49	The comparison of soil burial in 2 and 4 weeks for different lengths	138
4.50	SEM of the tensile failure surface of TPCS blended with the different fibre content of treated PALF for a single layer in 10 mm length (a) 20 wt.% (b) 50 wt.% (c) 60 wt.%	140
4.51	SEM of the tensile failure surface of TPCS blended with different fibre content of treated PALF for a single layer in 30mm length (a) 20 wt.% (b) 50 wt.% (c) 60 wt.%	140

LIST OF SYMBOLS AND ABBREVIATIONS

BFRP	- Biodegradable fibres reinforced polymer
CMC	- Ceramic matrix composite
CS	- Corn starch
EoB	- Elongation on break
FM	- Flexural modulus
FS	- Flexural strength
KOH	- Potassium hydroxide
LDPE	- Low-density polyethylene
MEKP	- Methyl-ethyl ketone peroxide
MMC	- Metal matrix composite
NaOH	- Sodium hydroxide
PALF	- Pineapple leaf fibre
PCL	- Polycaprolactone
PE	- Polyethylene
PHBV	- Polyhydroxybutyrate – co hydroxyvalerate
PLA	- Poly-lactic acid
PMC	- Polymer matrix composite
PP	- Polypropylene
PVA	- Polyvinyl alcohol
PVC	- Polyvinyl chloride
TBR	- Tapioca based bioplastic resin
TM	- Tensile modulus
TPCS	- Thermoplastics corn starch
TPS	- Thermoplastic starch
TS	- Tensile strength

LIST OF APPENDICES

A	Sample preparation	185
B	Mechanical testing	186
C	Physical testing	187



PTTA UTHM
PERPUSTAKAAN TUNKU TUN AMINAH

CHAPTER 1

INTRODUCTION

This section describes the background of the research and the significance of the research that has been performed. This section also represents the problem statement, research objectives, the scope of the study and the significance of the study.

1.1 Background study

Recently, biodegradable fibres reinforced polymer (BFRP), also known as natural fibre composite and it is becoming an interesting research topic for replacing conventional materials, particularly in the packaging industries, construction, furniture and automotive (Bachtiar et al., 2010; Jeffrey et al., 2011). The interest in developing a more environmentally friendly product is growing due to the accumulation of non - biodegradable waste in the landfill. As a result, several "green" materials have been developed to address this issue. The biopolymer derived from renewable resources is a promising alternative material for petroleum-based polymer, as they are biodegradable and therefore environmentally friendly compared to conventional polymers. Varying types of natural resources have been used to produce biopolymers ranging from lipids, proteins, celluloses and starches. Among these sources, starch is considered the most promising with enormous potential resource due to several aspects, such as renewable, low cost and completely biodegradable (Sahari et al., 2013). Starch can be transformed into thermoplastic starch (TPS) under the presence of heat and plasticizer which has similar process ability to traditional thermoplastics. The principal advantages for the production of this material are the thermoplasticity of this biopolymer. It makes manufacturing of this biopolymer using the traditional

processing equipment used for synthetic thermoplastics such as extruder and injection molding.

Natural fibres reinforced thermoplastic composites are a relatively new class of BFRP composite materials. This includes natural fibres such as jute, sisal, kenaf, bamboo and pineapple leaf and mixed with synthetic filler such as polypropylene (PP), polyethylene (PE), polyvinyl chloride (PVC) and vinyl ester. However, natural fibre has also been used to reinforce with natural filler such as seaweed, clay, talc and eggshell (Bootklad & Kaewtatip, 2013; Coativy et al., 2015; López et al., 2015). Recently, industries in the manufacturing sector are looking for new materials based on natural and renewable sources to be used in their products to reduce the environmental burden. The incorporation of natural material as reinforcement in polymer composites has produced a more environmentally friendly behaviour. Kengkhetkit & Amornsakchai (2014) mentioned that natural fibre composite production is becoming highly attractive and is widely practised due to global warming and oil depletion problems.

In addition, natural fibres in composite materials use less energy during processing, do not pose a health risk when inhaled, do not abrasive the system and reduce the consumption of petroleum resources (Phong et al., 2012; Vinod & Sudev, 2013). According to Selamat et al., (2014) natural fibres play an important role in the development of biodegradable composites to address the current environmental and ecological problems. Moreover, these green solutions would reduce the dependence of the manufacturing industry on synthetic materials such as glass fibres, which are often associated with a high risk potential for employees. Developing more environmentally friendly materials offers the manufacturing industry a new option for replacing the synthetic polymer in their production.

1.2 Problem statements

Nowadays, the high demand and consumption by the manufacturing industry of petroleum-based polymer produced serious environmental problems, particularly during the disposal phase. This disposal of waste is not readily biodegradable at the landfill or shore, because these waste contain dangerous chemicals which may damage the environment, biodiversity and human health (Maran et al., 2014). Moreover, the

use of petroleum-based polymer also will cause air pollution that contributes to global warming and oil resource depletion. Therefore, in recent years, many countries have restricted the use of plastic bags as a way of tackling this problem (López, Castillo, et al., 2015). Hence, this research aimed to resolve this problem by producing a 100% renewable and biodegradable polymer composite from sustainable materials.

Corn (also known as maize) is one of the world's primary starch sources. Corn starch derived from corn grain can be turned into a thermoplastic material which has a stiff property with heat and plasticizer. However, neat thermoplastic starch has drawbacks that hinder its use in commercial plastics industries such as poor mechanical strength and high susceptibility to water (Babaei et al., 2015). This restriction has limited the potential use of this resource in actual life. Therefore, adequate modifications should be applied to improve the characteristics of this material, such as reinforcing it with high potential natural fibres.

Natural fibres are more environmentally friendly than synthetic fibres, which are comparatively more expensive and have non - biodegradable attributes. In other terms, natural fibres have many unique properties, including such low cost, low density, environmentally friendly, biodegradable, specific strength properties and face minimum potential health risks (Pickering et al., 2016). The pineapple leaf fibre is one of the natural fibres that inspired researchers to explore its potential in composites as a strengthening material. (Todkar & Patil, 2019). PALF has several advantages as it grows rapidly and requires only several months to grow. Thus, after harvesting season, it is easy to recover and the pineapple leaf fibre is relatively stable compared to other natural fibres like cotton, kenaf and jute (Jawaid & Abdul Khalil, 2011). Furthermore, the pineapple leaf fibre is a traditional bio-resourced material that has not been wholly used and is also an abundant natural source in Johor, especially in pineapple plantations.

In addition, the combination of natural fibres such as pineapple leaf fibre with the petroleum-based polymer matrix would yield only partial biodegradable material. Hence, it is necessary to use pineapple leaf fibre as a reinforcement in polymer composites that use TPS as a matrix to create a fully biodegradable material. Therefore, the intention of this research are (1) to determine the best behaviours of thermoplastics corn starch (2) to tackle the incompatibility issue of pineapple leaf fibre reinforced composite (3) to widen the potential application of pineapple leaf fibre and

finally (4) the most important outcome is to create a completely biodegradable substance that can be disposed of securely in the environment.

1.3 Objectives

This research aims to develop and classify natural resource dependent biodegradable and renewable materials. Four principal goals of this research are:

1. To investigate the effect of different fibre types of untreated pineapple leaf fibre reinforced thermoplastic corn starch composites physical and mechanical behaviour at varying fibre loading.
2. To evaluate the behaviour of different fibre lengths of untreated pineapple leaf fibre reinforced thermoplastic corn starch composites physical and mechanical behaviour at varying fibre loading.
3. To compare the effect of treated and untreated pineapple leaf fibre reinforced thermoplastic corn starch composites physical and mechanical behaviour at varying fibre loading.
4. To evaluate the behaviour of different fibre lengths of treated pineapple leaf fibre reinforced thermoplastic corn starch composites physical and mechanical behaviour at varying fibre loading.

1.4 Scope of the study

This study attempts to get a deeper understanding of the characteristics of pineapple leaf fibre (PALF) reinforced thermoplastic corn starch (TPCS) in terms of, physical and mechanical behaviours due to the different fibres types, the different fibre lengths and the effect of treated PALF at varying fibre loading. The approach of this investigation is based on experimental studies. The study is categorized into three distinct phases.

The first phase of this study is the characterisation of maize starch. Corn starch used in this study was taken from the manufacturing type and in powder form. TPCS was produced using glycerol as a plasticizer. TPCS was compressed with four parameters to determine the appropriate compression moulding parameters, i.e. temperature, pressure, preheat period and compression length. The selected

temperature was between 150°C and 200°C, the pressure was between 10 kg/cm² and 30kg/cm², preheat duration was about 5 minutes to 20 minutes and compress duration was about 5 minutes to 20 minutes. TPCS was packed using seven different loadings of glycerol, which are 20%, 25%, 30%, 35%, 40%, 45% and 50%. Mechanical, physical and morphological characterizations were conducted.

The second phase of this study is to determine the effect of different types of fibres on the physical and mechanical behaviours of the PALF reinforced TPCS composite. Two different fibre types are the single layer (random orientation) and multi layers (laminates) were chosen for this study. Besides that's, two different fibre lengths, which are 2 mm and 10 mm were chosen to use in this phase. The results of these two different fibre types and two different lengths of PALF was measured, and the sample behaviour were experimentally observed. The best fibre types and length of PALF that gave the highest value of physical and mechanical behaviours were chosen for the next stage of this study.

The third phase emphasizes the influence of alkaline treatment on PALF. Treatment effects on the physical and mechanical behaviours of PALF reinforced TPCS as a polymer matrix were studied. In this analysis, Sodium Hydroxide (NaOH) was employed as the chemical to treat the PALF. In addition, two different fibre lengths, which are 10 mm and 30 mm were chosen to use in this phase. The results of untreated and treated PALF/TPCS bio-composites in two different lengths were compared.

The PALF used in this study was from Josapine cultivar and the PALF was bought from Pontian, Johor. PALF reinforced TPCS was fabricated with five different fibre loadings, which are 20%, 30%, 40%, 50% and 60%. The preparation of PALF/TPCS bio-composites samples was prepared using the compression moulding technique with random orientation of the PALF. The bio-composite specimens have been examined for their physical and mechanical behaviours. Tensile, flexural and impact experiments were carried out to determine the mechanical behaviour of PALF/TPCS bio-composites. Density, moisture content, moisture absorption, water absorption, soil burial and water solubility testing were conducted to analyse the physical behaviour of PALF/TPCS bio-composites. SEM analysis was carried out to analyse the PALF/TPCS bio-composites fracture behaviour.

1.5 Significance of the study

1. The results of the present study are expected to enhance the awareness of the development of a biodegradable polymer matrix from corn starch.
2. In this study, the production of the biodegradable polymer matrix with enhanced behaviour is expected to help address the environmental question of alternative materials for the petroleum-based polymer.
3. The issue of petroleum-based polymers, such as environmental pollution during production and disposal, can be mitigated by the use of entirely biodegradable and renewable polymer composites produced from TPCS and PALF.
4. In the area of waste management, this research explored the potential new application of PALF from Josapine cultivar reinforced TPCS for development bio-polymer composites.



PTTA UTHM
PERPUSTAKAAN TUNKU TUN AMINAH

CHAPTER 2

LITERATURE REVIEW

This section aims to explain the literature from this study further. This section comprises the previous research work on biodegradable fibres reinforce polymer (BFRP) composites, polymer matrix, thermoplastics starch, corn starch, natural fibre and pineapple leaf fibre (PALF). Findings from previous research and the objectives of this study are also discussed in this chapter.

2.1 Introduction

Previously, humans were aware of the function of composite materials. The records of composites which dated back to historical applications are utilized in construction applications. For instance, in countries like Africa and India, straw or husks like Figure 2.1 (a) were used with mud or clay to construct houses as shown in Figure 2.1 (b) and (c) and this been done for several hundred years (Khalafalla, Mohamad and Mayyuta, 2013). Straw or husks used in the process will provide the strength and structure while mud or clay will function as a binder and tie the straw together (Akinkurolere et al., 2006; Singh, Kumar, & Waghmare, 2016).



(a)



(b)



(c)

Figure 2.1: Building using straw and mud (Khalafalla, Mohamad & Mayyuta, 2013)

2.2 Composites

Generally, a composite material may be described as a combination of two or more materials in order to provide unique combined properties. As a whole, the integral materials will work together but still remain in their original forms and this will create the final properties of composite materials which are better than the fundamental material properties (Mazumdar, 2002). Elanchezhian et al. (2018) in their study stated that the composite is a combination of two materials in which one of them, defined as the reinforcing phase, is deposited in the form of fibres, sheets or crystals, and the other materials known as the matrix phase.

The reinforcing phase is the delivery step in the structure, through which other reinforcing products such as natural fibre, synthetic fibre, particle etc. were made available during that period (Santosh Kumar et al., 2015). Bunsell & Renard (2005) stated that fibres which are used as reinforcement could be divided into three groups which are regenerated, synthetic and natural. The natural fibres can be divided into three subgroups which are animal, vegetable and lastly mineral fibres as shown in Figure 2.2. According to Mazumdar (2002), the main functions of the fibres are (a) to carry the load in which the fibres carry 70 to 90% of the load, (b) to provide strength, stiffness, thermal stability and other structural properties and last but not least (c) to provide insulation or electrical conductivity depending on the type of fibre.

The matrix phase is also known as the composites continuous step and can be a polymer-metal or ceramic (Santosh Kumar et al., 2015). Based on this three basic metrics, the composite can be categorized into three common composite types: Polymer matrix composite (PMC), Metal matrix composite (MMC) and Ceramic matrix composite (CMC) composite as shown in Figure 2.3. However, the selection of matrix is based on the application, properties required and also method of the manufacturing processes (Kumar, Mohan, & Mahesha, 2015; Lau et al., 2018). Based on Mazumdar (2002), the matrix material fulfils several functions in a composite structure and the importance of a matrix material include the following: (a) binds the fibres together and transfers the load to the fibres.as as it also provides the shape and rigidity to the structure (b) isolates the fibres so that individual fibre can act separately. This will stop or slow down the crack propagation and (c) provides a better surface finishing quality and aids in the production of net-shape or near-net-shape parts as well

REFERENCES

- Abdal-Hay, A., Suardana, N. P. G., Jung, D. Y., Choi, K. S., & Lim, J. K. (2012). Effect of diameters and alkali treatment on the tensile properties of date palm fiber reinforced epoxy composites. *International Journal of Precision Engineering and Manufacturing*, 13(7), pp. 1199–1206.
- Aji, I. S., Zainudin, E. S., Abdan, K., Sapuan, S. M., & Khairul, M. D. (2013). Mechanical properties and water absorption behavior of hybridized kenaf/pineapple leaf fibre-reinforced high-density polyethylene composite. *Journal of Composite Materials*, 47(8), pp. 979–990.
- Akil, H. M., Cheng, L. W., Mohd Ishak, Z. A., Abu Bakar, A., & Abd Rahman, M. A. (2009). Water absorption study on pultruded jute fibre reinforced unsaturated polyester composites. *Composites Science and Technology*.
- Akinkulere, O. O., Jiang, C., Oyediran, A. T., Dele-Salawu, O. I., & Elensinnla, A. K. (2006). Engineering properties of Cob as a building material. In *Journal of Applied Sciences*, vol. 6. (8), pp. 1882–1885.
- Al-Oqla, F. M., & Sapuan, S. M. (2014). Natural fiber reinforced polymer composites in industrial applications: Feasibility of date palm fibers for sustainable automotive industry. *Journal of Cleaner Production*, 66, pp. 347–354.
- Alavudeen, A., Rajini, N., Karthikeyan, S., Thiruchitrambalam, M., & Venkateshwareen, N. (2015). Mechanical properties of banana/kenaf fiber-reinforced hybrid polyester composites: Effect of woven fabric and random orientation. *Materials and Design*.
- Alvarez, V. A., Fraga, A. N., & Va, A. (2003). Effects of the Moisture and Fiber Content on the Mechanical Properties of Biodegradable Polymer – Sisal.
- Ary Subagia, I. D. G., Kim, Y., Tijing, L. D., Kim, C. S., & Shon, H. K. (2014). Effect of stacking sequence on the flexural properties of hybrid composites reinforced with carbon and basalt fibers. *Composites Part B: Engineering*.

- Ashik, K. P., & Sharma, R. S. (2015). A Review on Mechanical Properties of Natural Fiber Reinforced Hybrid Polymer Composites. *Journal of Minerals and Materials Characterization and Engineering*, 03(05), pp. 420–426.
- Ashok Kumar, R. T., Mohan, N., & Mahesha, C. (2015). Sliding Wear Characteristics of Fiber Reinforced Fillers Filled Polymer Based Composites: A Review. *International Journal of Materials Science*, 10(January 2015), pp. 133–169.
- Asim, M., Abdan, K., Jawaid, M., Nasir, M., Dashtizadeh, Z., Ishak, M. R., & Hoque, M. E. (2015). A Review on Pineapple Leaves Fibre and Its Composites. *International Journal of Polymer Science*, pp. 1–16.
- Asim, M., Paridah, M. T., Saba, N., Jawaid, M., Alothman, O. Y., Nasir, M., & Almutairi, Z. (2018). Thermal, physical properties and flammability of silane treated kenaf/pineapple leaf fibres phenolic hybrid composites. *Composite Structures*, 202(February), pp. 1330–1338.
- ASTM D256-02 2002. Standard Test Methods for Determining the Izod Pendulum Impact Resistance of Plastics. American Society for Testing Materials.
- ASTM D638-00 2001. Standard Test Method for Tensile Properties of Plastics. American Society for Testing Materials.
- ASTM D790-00 2001. Standard Test Methods for Flexural Properties of Unreinforced and Reinforced Plastics and Electrical Insulating Materials. American Society for Testing Materials.
- Athijayamani, A., Thiruchitrabalam, M., Natarajan, U., & Pazhanivel, B. (2009). Effect of moisture absorption on the mechanical properties of randomly oriented natural fibers/polyester hybrid composite. *Materials Science and Engineering A*.
- Averous, L., & Boquillon, N. (2004). Biocomposites based on plasticized starch: Thermal and mechanical behaviours. *Carbohydrate Polymers*, 56(2), pp. 111–122.
- Aziz, S. H., & Ansell, M. P. (2004). The effect of alkalization and fibre alignment on the mechanical and thermal properties of kenaf and hemp bast fibre composites: Part 1 – polyester resin matrix. *Composites Science and Technology*, 64(9), pp. 1219–1230.
- Babaei, M., Jonoobi, M., Hamzeh, Y., & Ashori, A. (2015). Biodegradability and mechanical properties of reinforced starch nanocomposites using cellulose nanofibers. *Carbohydrate Polymers*, 132, pp. 1–8.

- Bachtiar, D., Sapuan, S. M., & Hamdan, M. M. (2009). The influence of alkaline surface fibre treatment on the impact properties of sugar palm fibre-reinforced epoxy composites. *Polymer - Plastics Technology and Engineering*, 48(4), pp. 379–383.
- Bachtiar, D., Sapuan, S. M., & Hamdan, M. M. (2010). Flexural properties of alkaline treated sugar palm fibre reinforced epoxy composites. *International Journal of Automotive and Mechanical Engineering*, 1(1), pp. 79–90.
- Bandyopadhyay, N. R., Sahoo, S., Ray, D., Das, K., Misra, M., & Mohanty, A. K. (2010). Physico-mechanical properties of the jute micro/nanofibril reinforced starch/polyvinyl alcohol biocomposite films. *Composites Part B: Engineering*, 42(3), pp. 376–381.
- Bénézet, J. C., Stanojlovic-Davidovic, A., Bergeret, A., Ferry, L., & Crespy, A. (2012). Mechanical and physical properties of expanded starch, reinforced by natural fibres. *Industrial Crops and Products*, 37(1), pp. 435–440.
- Bengtsson, M., Gatenholm, P., & Oksman, K. (2005). The effect of crosslinking on the properties of polyethylene/wood flour composites. *Composites Science and Technology*.
- Bennehalli, B., Sampathkumar, D., Punyamurth, R., & Venkateshappa, S. C. (2012). Effect of Esterification on Moisture Absorption of Single Areca Fiber. *International Journal of Agriculture Sciences*, 4(4), pp. 227–229.
- Bertuzzi, M. A., Armada, M., & Gottifredi, J. C. (2007). Physicochemical characterization of starch based films. *Journal of Food Engineering*, 82(1), pp. 17–25.
- Bisanda, E. T. N., & Ansell, M. P. (1991). The effect of silane treatment on the mechanical and physical properties of sisal-epoxy composites. *Composites Science and Technology*.
- Bodirlau, R., Teaca, C. A., & Spiridon, I. (2012). Influence of natural fillers on the properties of starch-based biocomposite films. *Composites Part B: Engineering*, 44(1), pp. 575–583.
- Boopathi, L., Sampath, P. S., & Mysamy, K. (2012). Investigation of physical, chemical and mechanical properties of raw and alkali treated Borassus fruit fiber. *Composites Part B: Engineering*.
- Bootklad, M., & Kaewtatip, K. (2013). Biodegradation of thermoplastic starch/eggshell powder composites. *Carbohydrate Polymers*, 97(2), pp. 315–320.

- Buléon, A., Colonna, P., Planchot, V., & Ball, S. (1998). Starch granules: structure and biosynthesis. *International Journal of Biological Macromolecules*, 23(2), pp. 85–112.
- Bunsell, A. R. and Renard, J. (2005). *Fundamentals of Fibre Reinforced Composite Materials*: Institute of Physics (IOP) Publishing.
- Cai, J., Xiong, Z., Zhou, M., Tan, J., Zeng, F., MeihuMa, Lin, S., & Xiong, H. (2014). Thermal properties and crystallization behavior of thermoplastic starch/poly(ϵ -caprolactone) composites. *Carbohydrate Polymers*, 102, pp. 746–754.
- Campos, A., Marconcini, J. M., Martins-Franchetti, S. M., & Mattoso, L. H. C. (2012). The influence of UV-C irradiation on the properties of thermoplastic starch and polycaprolactone biocomposite with sisal bleached fibers. *Polymer Degradation and Stability*, 97(10), pp. 1948–1955.
- Cao, Y., Shibata, S., & Fukumoto, I. (2006). Mechanical properties of biodegradable composites reinforced with bagasse fibre before and after alkali treatments. *Composites Part A: Applied Science and Manufacturing*.
- Castillo, L., López, O., López, C., Zaritzky, N., García, M. A., Barbosa, S., & Villar, M. (2013). Thermoplastic starch films reinforced with talc nanoparticles. *Carbohydrate Polymers*, 95(2), pp. 664–674.
- Cerqueira, M. A., Souza, B. W. S., Teixeira, J. A., & Vicente, A. A. (2012). Effect of glycerol and corn oil on physicochemical properties of polysaccharide films - A comparative study. *Food Hydrocolloids*, 27(1), pp. 175–184.
- Chandramohan, D., & Marimuthu, K. (2011). A Review on Natural Fibers. *IJRRAS*, 18(2).
- Chandramohan, D., & Presin Kumar, A. J. (2017). Experimental data on the properties of natural fiber particle reinforced polymer composite material. *Data in Brief*.
- Chang, Y. J., Choi, H. W., Kim, H. S., Lee, H., Kim, W., Kim, D. O., Kim, B. Y., & Baik, M. Y. (2013). Physicochemical properties of granular and non-granular cationic starches prepared under ultra high pressure. *Carbohydrate Polymers*, 99, pp. 385–393.
- Cherian, B. M., Leão, A. L., de Souza, S. F., Thomas, S., Pothan, L. A., & Kottaisamy, M. (2010). Isolation of nanocellulose from pineapple leaf fibres by steam explosion. *Carbohydrate Polymers*, 81(3), pp. 720–725.

- Chivrac, F., Angellier-Coussy, H., Guillard, V., Pollet, E., & Avérous, L. (2010). How does water diffuse in starch/montmorillonite nano-biocomposite materials? *Carbohydrate Polymers*, 82(1), pp. 128–135.
- Chollakup, R., Tantatherdtam, R., Ujjin, S., & Sriroth, K. (2010). Pineapple Leaf Fiber Reinforced Thermoplastic Composites: Effects of Fiber Length and Fiber Content on Their Characteristics. *Journal Of Applied Polymer Science*, 119, pp. 1952–1960.
- Chung, Y. L., & Lai, H. M. (2006). Molecular and granular characteristics of corn starch modified by HCl-methanol at different temperatures. *Carbohydrate Polymers*, 63(4), pp. 527–534.
- Coativy, G., Gautier, N., Pontoire, B., Buléon, A., Lourdin, D., & Leroy, E. (2015). Shape memory starch-clay bionanocomposites. *Carbohydrate Polymers*, 116, pp. 307–313.
- Da Róz, A. L., Ferreira, A. M., Yamaji, F. M., & Carvalho, A. J. F. (2012). Compatible blends of thermoplastic starch and hydrolyzed ethylene-vinyl acetate copolymers. *Carbohydrate Polymers*, 90(1), pp. 34–40.
- Dagade, P. C., & Shaikh, S. M. (2016). Effect of Fiber Length on Mechanical Properties of PALF Reinforced Bisphenol : A Composite. *International Journal of Innovations in Engineering Research and Technology*, 3(10), pp. 25–38.
- Danladi, A., & Shu'aib, J. (2014). Fabrication and Properties of Pineapple Fibre / High Density Polyethylene Composites. *American Journal of Materials Science*, 4(3), pp. 139–143.
- Danladi, Abdullahi, & Tunde, A. S. (2011). Effect of Fibre Length on the Physical and Mechanical Properties of Sisal / Polyethylene Composites. Properties of Sisal Fibres Composites. pp. 42–46.
- Das, G., & Biswas, S. (2016). Effect of fiber parameters on physical, mechanical and water absorption behaviour of coir fiber-epoxy composites. *Journal of Reinforced Plastics and Composites*, 35(8), pp. 628–637.
- Das, S., Rahman, M., & Hasan, M. (2018). Physico-Mechanical Properties of Pineapple Leaf and Banana Fiber Reinforced Hybrid Polypropylene Composites: Effect of Fiber Ratio and Sodium Hydroxide Treatment. *IOP Conference Series: Materials Science and Engineering*, 438(1).

- Devi, L. U., Bhagawan, S. S., & Thomas, S. (1996). Mechanical properties of pineapple leaf fiber-reinforced polyester composites. *Journal of Applied Polymer Science*, 64(9), pp. 1739–1748.
- Devi, L. U., Joseph, K., Nair, K. C. M., & Thomas, S. (2004). Ageing studies of pineapple leaf fiber-reinforced polyester composites. *Journal of Applied Polymer Science*, 94(2), pp. 503–510.
- Drzal, L. T., Mohanty, A. K., & Misra, M. (2001). Bio-Composite Materials As Alternatives To Petroleum-Based Composites for Automotive Applications. *Magnesium*, 40(60), pp. 1–3.
- Edhirej, A., Sapuan, S. M., Jawaidd, M., & Zahari, N. I. (2017). Preparation and characterization of cassava bagasse reinforced thermoplastic cassava starch. *Fibers and Polymers*, 18(1).
- El-Shekeil, Y. A., Sapuan, S. M., Jawaidd, M., & Al-Shuja'a, O. M. (2014). Influence of fiber content on mechanical, morphological and thermal properties of kenaf fibers reinforced poly(vinyl chloride)/thermoplastic polyurethane poly-blend composites. *Materials and Design*.
- Elanchezhian, C., Ramnath, B. V., Ramakrishnan, G., Rajendrakumar, M., Naveenkumar, V., & Saravanakumar, M. K. (2018). Review on mechanical properties of natural fiber composites. *Materials Today: Proceedings*, 5(1), pp. 1785–1790.
- Espert, A., Vilaplana, F., & Karlsson, S. (2004). Comparison of water absorption in natural cellulosic fibres from wood and one-year crops in polypropylene composites and its influence on their mechanical properties. *Composites Part A: Applied Science and Manufacturing*.
- Espinach, F. X., Delgado-Aguilar, M., Puig, J., Julian, F., Boufi, S., & Mutjé, P. (2015). Flexural properties of fully biodegradable alpha-grass fibers reinforced starch-based thermoplastics. *Composites Part B: Engineering*, 81, pp. 98–106.
- Ezema, I. C., Edelugo, S. O., & Omah, A. D. (2015). A Comparative Prediction of the Tensile Properties of Sisal Fiber Reinforced Epoxy Composite Using. *1(2011)*, pp. 9–18.
- Faruk, O., Bledzki, A. K., Fink, H. P., & Sain, M. (2012). Biocomposites reinforced with natural fibers: 2000-2010. *Progress in Polymer Science*, 37(11), pp. 1552–1596.

- Flores, A. C., Punzalan, E. R., & Ambangan, N. G. (2015). Effects of Kappa-Carrageenan on the Physico-Chemical Properties of Thermoplastic Starch. *Kimika*, 26(JANUARY), pp. 11–17.
- George, J., Bhagawan, S. S., Prabhakaran, N., & Thomas, S. (1995). Short Pineapple-Leaf-Fiber-Reinforced Low-Density Polyethylene Composites. *Journal of Applied Polymer Science*, 57, pp. 843–854.
- George, J., Bhagawan, S. S., & Thomas, S. (1998). Effects of environment on the properties of low-density polyethylene composites reinforced with pineapple-leaf fibre. *Composites Science and Technology*.
- Gironès, J., López, J. P., Mutjé, P., Carvalho, A. J. F., Curvelo, A. A. S., & Vilaseca, F. (2012). Natural fiber-reinforced thermoplastic starch composites obtained by melt processing. *Composites Science and Technology*, 72(7), pp. 858–863.
- Glória, G. O., Teles, M. C. A., Lopes, F. P. D., Vieira, C. M. F., Margem, F. M., Gomes, M. de A., & Monteiro, S. N. (2017). Tensile strength of polyester composites reinforced with PALF. *Journal of Materials Research and Technology*, 6(4), pp. 401–405.
- González, A., & Igarzabal, C. I. A. (2013). Soy protein e Poly (lactic acid) bilayer films as biodegradable material for active food packaging q. *Food Hydrocolloids*, 33(2), pp. 289–296.
- Gryszkin, A., Zięba, T., & Kapelko-Zeberska, M. (2016). Properties of corn starch subjected hydrothermal modification. *International Agrophysics*, 31(1), pp. 53–60.
- Guan, J., & Hanna, M. A. (2004). Extruding foams from corn starch acetate and native corn starch. *Biomacromolecules*, 5(6), pp. 2329–2339.
- Gutiérrez, T. J., Morales, N. J., Tapia, M. S., Pérez, E., & Famá, L. (2015). Corn Starch 80:20 “Waxy”:Regular, “Native” and Phosphated, as Bio-Matrixes for Edible Films. *Procedia Materials Science*, 8, pp. 304–310.
- Hamid, N. A., Abdullah, N. H. N., Mansor, M. R., Rosli, M. A. M., & Akop, M. Z. (2009). An Experimental Study of The Influence of Fiber Architecture on The Strength of Polymer Composite Material. *Journal of Mechanical Engineering and Technology (JMET)*, 2(2).

- Hariwongsanupab, N., Thanawan, S., Amornsakchai, T., Vallat, M. F., & Mougin, K. (2017). Improving the mechanical properties of short pineapple leaf fiber reinforced natural rubber by blending with acrylonitrile butadiene rubber. *Polymer Testing*, 57, pp. 94–100.
- Hashim, M. Y., Roslan, M. N., Amin, A. M., Mujahid, A., & Zaidi, A. (2012). Mercerization Treatment Parameter Effect on Natural Fiber Reinforced Polymer Matrix Composite : A Brief Review. *World Academy of Science, Engineering and Technology*, 6(8), pp. 1638–1644.
- Hu, R., Sun, M., & Lim, J. (2010). Moisture absorption, tensile strength and microstructure evolution of short jute fiber/polylactide composite in hygrothermal environment. *Materials and Design*, 31(7), pp. 3167–3173.
- Huang, M. F., Yu, J. G., & Ma, X. F. (2004). Studies on the properties of Montmorillonite-reinforced thermoplastic starch composites. *Polymer*.
- Huang, M., & Yu, J. (2006). Structure and properties of thermoplastic corn starch/montmorillonite biodegradable composites. *Journal of Applied Polymer Science*, 99(1), pp. 170–176.
- Huda, M. S., Drzal, L. T., Mohanty, A. K., & Misra, M. (2008). Effect of chemical modifications of the pineapple leaf fiber surfaces on the interfacial and mechanical properties of laminated biocomposites. *Composite Interfaces*, 15(2–3), pp. 169–191.
- Ibrahim, H., Farag, M., Megahed, H., & Mehanny, S. (2014). Characteristics of starch-based biodegradable composites reinforced with date palm and flax fibers. *Carbohydrate Polymers*, 101(1), pp. 11–19.
- Ibrahim, H., Faraq, M., Megahed, H., & Sherif Mehanny. (2013). Characteristics of starch-based composites reinforced with date palm and flax fibers. *Carbohydrate Polymers*, 101, pp. 11–19.
- Ibrahim, M. S., Sapuan, S. M., & Faieza, A. A. (2012). Mechanical and Thermal Properties of Composites From Unsaturated Polyester Filled With Oil Palm Ash. 2(June), pp. 133–147.
- Indra Reddy, M., Anil Kumar, M., & Rama Bhadri Raju, C. (2018). Tensile and Flexural properties of Jute, Pineapple leaf and Glass Fiber Reinforced Polymer Matrix Hybrid Composites. *Materials Today: Proceedings*, 5(1), pp. 458–462.

- Isiaka Oluwole, O., Michael Seun, O., & Sunday Joseph, O. (2015). Influence of Chemical Treatment on the Constituents and Tensile Properties of Selected Agro-Fibres. *The West Indian Journal of Engineering*, 38(2), pp. 4–12.
- Jack R. Vinson & Robert L. Sierakowski (2008). *The Behavior of Structures Composed of Composite Materials*. 2nd ed. Netherlands: Springer.
- Jamil, N. H., Norizan, L., & Kosnan, N. M. (2014). A Study on Types of Pineapple Leaf Fibres (PALF) Reinforced Polyactide (PLA). pp. 1–6.
- Jang, J., & Moon, S. I. (1995). Impact behavior of carbon fiber/ultra-high modulus polyethylene fiber hybrid composites. *Polymer Composites*, 16(4), pp. 325–329.
- Jannah, M., Mariatti, M., Abu Bakar, A., & Abdul Khalil, H. P. S. (2009). Effect of chemical surface modifications on the properties of woven banana-reinforced unsaturated polyester composites. *Journal of Reinforced Plastics and Composites*, 28(12), pp. 1519–1532.
- Jawaid, M., & Abdul Khalil, H. P. S. (2011). Cellulosic/synthetic fibre reinforced polymer hybrid composites: A review. *Carbohydrate Polymers*, 86(1), pp. 1–18.
- Jawaid, M., Abdul Khalil, H. P. S., & Abu Bakar, A. (2010). Mechanical performance of oil palm empty fruit bunches/jute fibres reinforced epoxy hybrid composites. *Materials Science and Engineering A*, 527(29–30), pp. 7944–7949.
- Jawaid, M., Abdul Khalil, H. P. S., & Abu Bakar, A. (2011). Woven hybrid composites: Tensile and flexural properties of oil palm-woven jute fibres based epoxy composites. *Materials Science and Engineering A*, 528(15), pp. 5190–5195.
- Jawaid, M., Abdul Khalil, H. P. S., Noorunnisa Khanam, P., & Abu Bakar, A. (2011). Hybrid Composites Made from Oil Palm Empty Fruit Bunches/Jute Fibres: Water Absorption, Thickness Swelling and Density Behaviours. *Journal of Polymers and the Environment*, 19(1), pp. 106–109.
- Jeffrey, K. J. T., Tarlochan, F., & Rahman, M. M. (2011). Composite Structures : Effect of Temperature and Water. *International Journal of Automotive and Mechanical Engineering*, 4(December), pp. 504–519.
- John, M. J., & Anandjiwala, R. D. (2016). Polyvinyl Alcohol-Modified Pithecellobium Clypearia Benth Herbal Residue FiberPolypropylene Composites. *Polymer Composites*, 37(1), pp. 915–924.
- John, M. J., & Thomas, S. (2008). Biofibres and biocomposites. *Carbohydrate Polymers*, 71(3), pp. 343–364.

- Jose, S., Salim, R., & Ammayappan, L. (2016). An Overview on Production, Properties, and Value Addition of Pineapple Leaf Fibers (PALF). *Journal of Natural Fibers*, 13(3), pp. 362–373.
- Jumaidin, R., Sapuan, S. M., Jawaidd, M., Ishak, M. R., & Sahari, J. (2016). Characteristics of thermoplastic sugar palm Starch/Agar blend: Thermal, tensile, and physical properties. *International Journal of Biological Macromolecules*, 89, pp. 575–581.
- Jumaidin, R., Sapuan, S. M., Jawaidd, M., Ishak, M. R., & Sahari, J. (2017). Characteristics of Eucheuma cottonii waste from East Malaysia: physical, thermal and chemical composition. *European Journal of Phycology*, 52(2), pp. 200–207.
- Jumaidin, Ridhwan, Sapuan, S. M., Jawaidd, M., Ishak, M. R., & Sahari, J. (2017a). Effect of seaweed on mechanical, thermal, and biodegradation properties of thermoplastic sugar palm starch/agar composites. *International Journal of Biological Macromolecules*, 99, pp. 265–273.
- Jumaidin, Ridhwan, Sapuan, S. M., Jawaidd, M., Ishak, M. R., & Sahari, J. (2017b). Thermal, mechanical, and physical properties of seaweed/sugar palm fibre reinforced thermoplastic sugar palm Starch/Agar hybrid composites. *International Journal of Biological Macromolecules*, 97, pp. 606–615.
- Kabir, M. M., Wang, H., Aravinthan, T., Cardona, F., & Lau, K.-T. (2007). Effects of Natural Fibre Surface on Composite Properties : A Review. *Energy, Environment and Sustainability*, pp. 94–99.
- Kabir, M. M., Wang, H., Lau, K. T., & Cardona, F. (2012). Chemical treatments on plant-based natural fibre reinforced polymer composites: An overview. *Composites Part B: Engineering*.
- Kaewpirom, S., & Worrarat, C. (2014). Preparation and properties of pineapple leaf fiber reinforced poly(lactic acid) green composites. *Fibers and Polymers*, 15(7), pp. 1469–1477.
- Kakroodi, A. R., Cheng, S., Sain, M., & Asiri, A. (2014). Mechanical, thermal, and morphological properties of nanocomposites based on polyvinyl alcohol and cellulose nanofiber from Aloe vera rind. *Journal of Nanomaterials*, 2014(i), pp. 12–18.

- Kalambettu, A., Damodaran, A., Dharmalingam, S., & Vallam, M. T. (2015). Evaluation of Biodegradation of Pineapple Leaf Fiber Reinforced PVA Composites. *Journal of Natural Fibers*, 12(1), pp. 39–51.
- Kalapakdee, A., & Amornsakchai, T. (2014). Mechanical properties of preferentially aligned short pineapple leaf fiber reinforced thermoplastic elastomer: Effects of fiber content and matrix orientation. *Polymer Testing*, 37, pp. 36–44.
- Kalia, S., Dufresne, A., Cherian, B. M., Kaith, B. S., Avérous, L., Njuguna, J., & Nassiopoulou, E. (2011). Cellulose-based bio- and nanocomposites: A review. *International Journal of Polymer Science*.
- Kalia, S., Kaith, B. S., & Kaur, I. (2009). Pretreatments of Natural Fibers and their Application as Reinforcing Material in Polymer Composites—A Review. *Polymer Engineering and Science*, pp. 1253–1272.
- Kanmani, P., & Rhim, J. (2014). Antimicrobial and physical-mechanical properties of agar-based films incorporated with grapefruit seed extract. *102*, pp. 708–716.
- Kasim, A. N., Selamat, M. Z., Daud, M. A. M., Yaakob, M. Y., Putra, A., & Sivakumar, D. (2016). Mechanical properties of polypropylene composites reinforced with alkaline treated pineapple leaf fibre from josapine cultivar. *International Journal of Automotive and Mechanical Engineering*, 13(1), pp. 3157–3167.
- Kengkhethit, N., & Amornsakchai, T. (2014). A new approach to “Greening” plastic composites using pineapple leaf waste for performance and cost effectiveness. *Materials and Design*, 55, pp. 292–299.
- Kesarwani, P., Jahan, S., & Kesarwani, K. (2015). Composites : Classification and its manufacturing process. *International Journal of Applied Research*, 1(9), pp. 352–358.
- Khalafalla, Mohamad and Mayyuta, D. (2013). Review of different construction and building materials used before 21st century in Africa compared to the present situation after 21st century. pp. 1–30.
- Khalil, H. P. S. A., Alwani, M. S., & Omar, A. K. M. (2006). Chemical composition, anatomy, lignin distribution, and cell wall structure of Malaysian plant waste fibers. *BioResources*, 1(2), pp. 220–232.

- Khalil, H. P. S. A., Noriman, N. Z., Ahmad, M. N., Ratnam, M. M., & Fuaad, N. A. N. (2007). Polyester composites filled carbon black and activated carbon from bamboo (*gigantochloa scortechinii*): Physical and mechanical properties. *Journal of Reinforced Plastics and Composites*, 26(3), pp. 305–320.
- Koronis, G., Silva, A., & Fontul, M. (2013). Green composites: A review of adequate materials for automotive applications. *Composites Part B: Engineering*, 44(1), pp. 120–127.
- Krzyzak, A., Mazur, M., Gajewski, M., Drozd, K., Komorek, A., & Przybyłek, P. (2016). Sandwich Structured Composites for Aeronautics: Methods of Manufacturing Affecting Some Mechanical Properties. *International Journal of Aerospace Engineering*.
- Kumar, R., Obrai, S., & Sharma, A. (2011). Chemical modifications of natural fiber for composite material. *Pelagia Research Library*, 2(4), pp. 219–228.
- Lau, K. tak, Hung, P. yan, Zhu, M. H., & Hui, D. (2018). Properties of natural fibre composites for structural engineering applications. *Composites Part B: Engineering*, pp. 222–233.
- Lee, H. S., Cho, D., & Han, S. O. (2008). Effect of natural fiber surface treatments on the interfacial and mechanical properties of henequen/polypropylene biocomposites. *Macromolecular Research*, 16(5), pp. 411–417.
- Leman, Z., Sapuan, S. ., Azwan, M., Ahmad, M. M. H. M., & Maleque, M. A. (2008). The Effect of Environmental Treatments on Fiber Surface Properties and Tensile Strength of Sugar Palm Fiber-Reinforced Epoxy Composite. *Polymer-Plastics Technology and Engineering*, 47(6), pp. 606–612.
- Leman, Z., Sapuan, S. M., Saifol, A. M., Maleque, M. A., & Ahmad, M. M. H. M. (2008). Materials & Design Moisture absorption behavior of sugar palm fiber reinforced epoxy composites. 29, pp. 1666–1670.
- Li, J., Luo, X., Lin, X., & Zhou, Y. (2013). Comparative study on the blends of PBS/thermoplastic starch prepared from waxy and normal corn starches. *Starch/Staerke*, 65(9–10), pp. 831–839.
- Li, X., Tabil, L. G., & Panigrahi, S. (2007a). Chemical treatments of natural fiber for use in natural fiber-reinforced composites: A review. *Journal of Polymers and the Environment*, 15(1), pp. 25–33.
- Liu, J., Jia, C., & He, C. (2012). Rice Straw and Cornstarch Biodegradable Composites. *AASRI Procedia*, 3, pp. 83–88.

- Liu, L., Yu, J., Cheng, L., & Yang, X. (2009). Biodegradability of poly(butylene succinate) (PBS) composite reinforced with jute fibre. *Polymer Degradation and Stability*.
- Liu, W., Misra, M., Askeland, P., Drzal, L. T., & Mohanty, A. K. (2005). "Green" composites from soy based plastic and pineapple leaf fiber: Fabrication and properties evaluation. *Polymer*, 46(8), pp. 2710–2721.
- Lobo, M. G., & Siddiq, M. (2017). Overview of pineapple production, postharvest physiology, processing and nutrition. *Handbook of Pineapple Technology: Postharvest Science, Processing and Nutrition*, pp. 1–15.
- Lopattananon, N., Payae, Y., & Seadan, M. (2008). Influence of Fiber Modification on Interfacial Adhesion and Mechanical Properties of Pineapple Leaf Fiber-Epoxy Composites. *Journal of Applied Polymer Science*, 110, pp. 433–443.
- Lopattananon, Natinee, Panawarangkul, K., Sahakaro, K., & Ellis, B. (2006). Performance of pineapple leaf fiber-natural rubber composites: The effect of fiber surface treatments. *Journal of Applied Polymer Science*, 102(2), pp. 1974–1984.
- Lopez, O., Rodriguez, M. S., Villar, M. A., Garcia, M. A., Gentili, A., & Albertengo, L. (2014). Thermo-compression of biodegradable thermoplastic corn starch films containing chitin and chitosan. *LWT - Food Science and Technology*, 57(1), pp. 106–115.
- López, O., Zaritzky, N., Castillo, L., Barbosa, S., Villar, M., & García, M. A. (2015). Talc Nanoparticles Influence on Thermoplastic Corn Starch Film Properties. *Procedia Materials Science*, 8, pp. 338–345.
- López, O. V., Castillo, L. A., García, M. A., Villar, M. A., & Barbosa, S. E. (2015). Food packaging bags based on thermoplastic corn starch reinforced with talc nanoparticles. *Food Hydrocolloids*, 43, pp. 18–24.
- Lu, N., & Oza, S. (2013). A comparative study of the mechanical properties of hemp fiber with virgin and recycled high density polyethylene matrix. *Composites Part B: Engineering*.
- Luo, S., & Netravali, A. N. (1999a). Interfacial and mechanical properties of environment-friendly 'green' composites made from pineapple fibers and poly(hydroxybutyrate-co-valerate) resin. *Journal of Materials Science*, 4, pp. 3709–3719.

- Luo, S., & Netravali, A. N. (1999b). Mechanical and Thermal Properties of Environment-Friendly “Green” Composites Made From Pineapple Leaf Fibers and Poly(hydroxybutyrate-co-valerate) Resin. *Polymer Composites*, 20, pp. 367–378.
- Ma, X. F., Yu, J. G., & Wan, J. J. (2006). Urea and ethanolamine as a mixed plasticizer for thermoplastic starch. *Carbohydrate Polymers*, 64(2), pp. 267–273.
- Magalhães, N. F., & Andrade, C. T. (2009). Thermoplastic corn starch/clay hybrids: Effect of clay type and content on physical properties. *Carbohydrate Polymers*, 75(4), pp. 712–718.
- Mangal, R., Saxena, N. S., Sreekala, M. S., Thomas, S., & Singh, K. (2003). Thermal properties of pineapple leaf fiber reinforced composites. *Materials Science and Engineering A*, 339(1–2), pp. 281–285.
- Mano, J. F., Koniarova, D., & Reis, R. L. (2003). Thermal properties of thermoplastic starch/synthetic polymer blends with potential biomedical applicability. *Journal of Materials Science: Materials in Medicine*, 14(2), pp. 127–135.
- Manríquez-González, R., Iwakiri, S., Flores-Sahagun, T. S., de Muniz, G. B., Kestur, S. G., & Lomeli-Ramírez, M. G. (2013). Bio-composites of cassava starch-green coconut fiber: Part II—Structure and properties. *Carbohydrate Polymers*, 102, pp. 576–583.
- Maran, J. P., Sivakumar, V., Sridhar, R., & Thirugnanasambandham, K. (2013). Development of model for barrier and optical properties of tapioca starch based edible films. *Carbohydrate Polymers*, 92(2), pp. 1335–1347.
- Maran, J. P., Sivakumar, V., Thirugnanasambandham, K., & Sridhar, R. (2014). Degradation behavior of biocomposites based on cassava starch buried under indoor soil conditions. *Carbohydrate Polymers*, 101(1), pp. 20–28.
- Martins, A. B., & Santana, R. M. C. (2016). Effect of carboxylic acids as compatibilizer agent on mechanical properties of thermoplastic starch and polypropylene blends. *Carbohydrate Polymers*, 135, pp. 79–85.
- Mathivanan, D., Norfazilah, H., Siregar, J. P., Rejab, M. R. M., Bachtiar, D., & Cionita, T. (2016). The study of mechanical properties of pineapple leaf fibre reinforced tapioca based bioplastic resin composite. *MATEC Web of Conferences*, 74, 00016.
- Matthews, F. L. and Rawlings, R.D. (1999). *Composite Materials: Engineering and Science*: CRC Press.

- Mendes, J. F., Paschoalin, R. T., Carmona, V. B., Sena Neto, A. R., Marques, A. C. P., Marconcini, J. M., Mattoso, L. H. C., Medeiros, E. S., & Oliveira, J. E. (2016). Biodegradable polymer blends based on corn starch and thermoplastic chitosan processed by extrusion. *Carbohydrate Polymers*, 137, pp. 452–458.
- Mishra, S., Misra, M., Tripathy, S. S., Nayak, S. K., & Mohanty, A. K. (2001). Potentiality of pineapple leaf fibre as reinforcement in PALF-polyester composite: Surface modification and mechanical performance. *Journal of Reinforced Plastics and Composites*, 20(4), pp. 321–334.
- Mishra, S., Mohanty, A. K., Drzal, L. T., Misra, M., Parija, S., Nayak, S. K., & Tripathy, S. S. (2003). Studies on mechanical performance of biofibre/glass reinforced polyester hybrid composites. *Composites Science and Technology*.
- Mishra, Supriya, Mohanty, A. K., Drzal, L. T., Misra, M., & Hinrichsen, G. (2004). A review on pineapple leaf fibers, sisal fibers and their biocomposites. *Macromolecular Materials and Engineering*, 289(11), pp. 955–974.
- Mohamed, A. R., Sapuan, S. M., & Khalina, A. (2010). Selected properties of hand-laid and compression molded vinyl ester and pineapple leaf fiber (PALF)-reinforced vinyl ester composites. *International Journal of Mechanical and Materials Engineering*, 5(1), pp. 68–73.
- Mohamed, A. R., Sapuan, S. M., Shahjahan, M., & Khalina, A. (2009). Characterization of pineapple leaf fibers from selected Malaysian cultivars. *Journal of Food, Agriculture & Environment*, 7, pp. 235–240.
- Mohammed, L., Ansari, M. N. M., Pua, G., Jawaaid, M., & Islam, M. S. (2015). A Review on Natural Fiber Reinforced Polymer Composite and Its Applications.
- Mohantya, A. K., Misra, M., & Hinrichsen, G. (2000). Biofibres, biodegradable polymers and biocomposites: An overview. *Macromolecular Materials and Engineering*, 56(2), pp. 276–277.
- Mohsin, M., Hossin, A., & Haik, Y. (2011). Thermal and Mechanical Properties of Poly(vinyl alcohol) Plasticized with Glycerol. *Journal of Applied Polymer Science*, 122, pp. 3102–3109.
- Mukherjee, P. S., & Satyanarayana, K. G. (1986). An empirical evaluation of structure-property relationships in natural fibres and their fracture behaviour. *Journal of Materials Science*, 21(12), pp. 4162–4168.

- Müller, P., Renner, K., Móczó, J., Fekete, E., & Pukánszky, B. (2014). Thermoplastic starch/wood composites: Interfacial interactions and functional properties. *Carbohydrate Polymers*, 102(1), pp. 821–829.
- Munawar, R. F., Jamil, N. H., Shahril, M. K., Skh Abdul Rahim, S. M., Zainal Abidin, M. Z., Azam, M. A., & Lau, K. T. (2015). Development of Green Composite: Pineapple Leaf Fibers (PALF) Reinforced Polylactide (PLA). *Applied Mechanics and Materials*, 761(May 2015), pp. 520–525.
- Mwaikambo, L. Y., & Ansell, M. P. (2002). Chemical modification of hemp, sisal, jute, and kapok fibers by alkalization. *Journal of Applied Polymer Science*, 84(12), pp. 2222–2234.
- Mylsamy, K., & Rajendran, I. (2010). Investigation on physio-chemical and mechanical properties of raw and alkali-treated Agave americana fiber. *Journal of Reinforced Plastics and Composites*, 29(19), pp. 2925–2935.
- Nadhari, W. N. A. W., Hashim, R., Hiziroglu, S., Sulaiman, O., Boon, J. G., Salleh, K. M., Awalludin, M. F., Sato, M., & Sugimoto, T. (2014). Measurement of some properties of binderless composites manufactured from oil palm trunks and Acacia mangium. *Measurement: Journal of the International Measurement Confederation*, 50(1), pp. 250–254.
- Nadlene, R., Sapuan, S. M., Jawaid, M., Ishak, M. R., & Yusriah, L. (2015a). A Study on Chemical Composition, Physical, Tensile, Morphological, and Thermal Properties of Roselle Fibre: Effect of Fibre Maturity. *BioResources*, 10(1), pp. 1803–1823.
- Nadlene, R., Sapuan, S. M., Jawaid, M., Ishak, M. R., & Yusriah, L. (2015b). Material characterization of roselle fibre (*Hibiscus sabdariffa* L.) as potential reinforcement material for polymer composites. *Fibres and Textiles in Eastern Europe*, 23(6), pp. 23–30.
- Nadlene, R., Sapuan, S. M., Jawaid, M., Ishak, M. R., & Yusriah, L. (2016). The Effects of Chemical Treatment on the Structural and Thermal, Physical, and Mechanical and Morphological Properties of Roselle Fiber-Reinforced Vinyl Ester Composites. *Polymer Composites*, 36, pp. 1230–1241.
- Nafchi, A. M., Moradpour, M., Saeidi, M., & Alias, A. K. (2013). Thermoplastic starches: Properties, challenges, and prospects. *Starch/Staerke*, 65(1–2), pp. 61–72.

- Neto, A. R. S., Claro, P. I. C., Souza, F. V.D., Mattoso, L. H. C., & Marconcini, J. M. (2017). Poly(lactic acid) composites reinforced with leaf fibers from ornamental variety of hybrid pineapple (Potyra). *Polymer Composites*, pp. 915–924.
- Nopparut, A., & Amornsakchai, T. (2016). Influence of pineapple leaf fiber and it's surface treatment on molecular orientation in, and mechanical properties of, injection molded nylon composites. *Polymer Testing*, 52, pp. 141–149.
- Onyeagoro, G. (2012). Effect of Chemical Treatment on The Constituents and Tensile Properties of Oil Palm Leaf Fibre. *Academic Research International*, 2(3), pp. 88.
- Ortega-Toro, R., Morey, I., Talens, P., & Chiralt, A. (2015). Active bilayer films of thermoplastic starch and polycaprolactone obtained by compression molding. *Carbohydrate Polymers*, 127, pp. 282–290.
- Pan, Y., & Zhong, Z. (2014). Modeling of the mechanical degradation induced by moisture absorption in short natural fiber reinforced composites. *Composites Science and Technology*, 103, pp. 22–27.
- Panyasart, K., Chaiyut, N., Amornsakchai, T., & Santawitee, O. (2014). Effect of surface treatment on the properties of pineapple leaf fibers reinforced polyamide 6 composites. *Energy Procedia*, 56(C), pp. 406–413.
- Paul, A. F., Hughes, J. M., & Robert, M. E. (2007). Review Biocomposites: technology, environmental credentials and market forces. *Journal of the Science of Food and Agriculture*, 87(2), pp. 930–944.
- Perez, S., Baldwin, P. M., & Gallant, D. J. (2009). Structural Features of Starch Granules I. In *Starch: Chemistry and Technology, Third Edition* (Third Edit, Issue March). Elsevier Inc.
- Phong, N. T., Fujii, T., Chuong, B., & Okubo, K. (2012). Study on How to Effectively Extract Bamboo Fibers from Raw Bamboo and Wastewater Treatment. *Journal of Materials Science Research*, 1(1), pp. 144–155.
- Pickering, K. L., Efendy, M. G. A., & Le, T. M. (2016). A review of recent developments in natural fibre composites and their mechanical performance. In *Composites Part A: Applied Science and Manufacturing*.
- Pittayavinai, P., Thanawan, S., & Amornsakchai, T. (2016). Manipulation of mechanical properties of short pineapple leaf fiber reinforced natural rubber composites through variations in cross-link density and carbon black loading. *Polymer Testing*, 54, pp. 84–89.

- Potluri, R., Diwakar, V., Venkatesh, K., & Srinivasa Reddy, B. (2018). Analytical Model Application for Prediction of Mechanical Properties of Natural Fiber Reinforced Composites. *Materials Today: Proceedings*, 5(2), pp. 5809–5818.
- Prachayawarakorn, J., Limsiriwong, N., Kongjindamunee, R., & Surakit, S. (2012). Effect of Agar and Cotton Fiber on Properties of Thermoplastic Waxy Rice Starch Composites. *Journal of Polymers and the Environment*, 20(1), pp. 88–95.
- Prachayawarakorn, J., Sangnitdej, P., & Boonpasith, P. (2010). Properties of thermoplastic rice starch composites reinforced by cotton fiber or low-density polyethylene. *Carbohydrate Polymers*, 81(2), pp. 425–433.
- Prachayawarakorn, Jutarat, Chaiwatyothin, S., Mueangta, S., & Hanchana, A. (2013). Effect of jute and kapok fibers on properties of thermoplastic cassava starch composites. *Materials and Design*, 47, pp. 309–315.
- Prachayawarakorn, Jutarat, Ruttanabus, P., & Boonsom, P. (2011). Effect of Cotton Fiber Contents and Lengths on Properties of Thermoplastic Starch Composites Prepared from Rice and Waxy Rice Starches. *Journal of Polymers and the Environment*, 19(1), pp. 274–282.
- Priya, B., Gupta, V. K., Pathania, D., & Singha, A. S. (2014). Synthesis, characterization and antibacterial activity of biodegradable starch/PVA composite films reinforced with cellulosic fibre. *Carbohydrate Polymers*, 109, pp. 171–179.
- Priyanka, P., Dixit, A., & Mali, H. S. (2017). High-Strength Hybrid Textile Composites with Carbon, Kevlar, and E-Glass Fibers for Impact-Resistant Structures. A Review. *Mechanics of Composite Materials*, 53(5), pp. 685–704.
- Prukkaewkanjana, K., Thanawan, S., & Amornsakchai, T. (2015). High performance hybrid reinforcement of nitrile rubber using short pineapple leaf fiber and carbon black. *Polymer Testing*, 45, pp. 76–82.
- Pushpadassa, H. A., Kumara, A., Jacksonb, D. S., Wehlingb, R. L., Dumaisc, J. J., & Hannaa, M. A. (2009). Macromolecular changes in extruded starch-films plasticized with glycerol, water and stearic acid. *Starch/Staerke*, 61(5), pp. 256–266.
- Rahman, M. A. (2011). Study on modified pineapple leaf fiber. *Journal of Textile and Apparel, Technology and Management*, 7(2), pp. 1–16.

- Rajesh, G., Siripurapu, G., & Lella, A. (2018). Evaluating Tensile Properties of Successive Alkali Treated Continuous Pineapple Leaf Fiber Reinforced Polyester Composites. *Materials Today: Proceedings*, 5(5), pp. 13146–13151.
- Ramadevi, P., Sampathkumar, D., Srinivasa, C. V., & Bennehalli, B. (2012). Effect of alkali treatment on water absorption of single cellulosic abaca fiber. *BioResources*, 7(3), pp. 3515–3524.
- Ramanaiah, K., Ratna Prasad, A. V., & Hema Chandra Reddy, K. (2012). Effect of fiber loading on mechanical properties of borassus seed shoot fiber reinforced polyester composites. *Journal of Materials and Environmental Science*, 3(2), pp. 374–378.
- Ramesh, S., Shanti, R., & Morris, E. (2011). Studies on the plasticization efficiency of deep eutectic solvent in suppressing the crystallinity of corn starch based polymer electrolytes. *Carbohydrate Polymers*, 87(1), pp. 701–706.
- Ramírez, M. G. L., Satyanarayana, K. G., Iwakiri, S., Muniz, G. B. de, Tanobe, V., & Flores-Sahagun, T. S. (2011). Study of the properties of biocomposites. Part I. Cassava starch-green coir fibers from Brazil. *Carbohydrate Polymers*, 86(4), pp. 1712–1722.
- Ramli, S. N. R., Md. Fadzullah, S. H. S., & Mustafa, Z. (2017). The Effect Of Alkaline Treatment And Fiber Length On Pineapple Leaf Fiber Reinforced Lactic Acid. *Jurnal Teknologi*, 79(4–2), pp. 111–115.
- Ray, S. S., & Bousmina, M. (2005). Biodegradable polymers and their layered silicate nanocomposites: In greening the 21st century materials world. *Progress in Materials Science*, 50(8), pp. 962–1079.
- Razali, N., Sapuan, S. M., Jawaid, M., Ishak, M. R., & Lazim, Y. (2016). Mechanical and Thermal Properties of Roselle Fibre Reinforced Vinyl Ester Composites. *BioResources*, 11(4), pp. 9325–9339.
- Rosa, D. dos S., & Lenz, D. M. (2013). Biocomposites: Influence of Matrix Nature and Additives on the Properties and Biodegradation Behaviour. *Intech, i(tourism)*, pp. 433–475.
- Rosa, R. C. R. S., & Andrade, C. T. (2004). Effect of Chitin Addition on Injection-Molded Thermoplastic Corn Starch. *Journal of Applied Polymer Science*, 92(4), pp. 2706–2713.

- Sabetzadeh, M., Bagheri, R., & Masoomi, M. (2016). Effect of nanoclay on the properties of low density polyethylene/linear low density polyethylene/thermoplastic starch blend films. *Carbohydrate Polymers*, 141, pp. 75–81.
- Sahari, J., Sapuan, S. M., Zainudin, E. S., & Maleque, M. A. (2012). A New Approach to Use Arenga Pinnata as Sustainable Biopolymer: Effects of Plasticizers on Physical Properties. *Procedia Chemistry*, 4, pp. 254–259.
- Sahari, J., Sapuan, S. M., Zainudin, E. S., & Maleque, M. A. (2013a). Mechanical and thermal properties of environmentally friendly composites derived from sugar palm tree. *Materials and Design*, 49, pp. 285–289.
- Sahari, J., Sapuan, S. M., Zainudin, E. S., & Maleque, M. A. (2013b). Thermo-mechanical behaviors of thermoplastic starch derived from sugar palm tree (Arenga pinnata). *Carbohydrate Polymers*, 92(2), pp. 1711–1716.
- Sahari, J., Sapuan, S. M., Zainudin, E. S., & Maleque, M. A. (2014). Physico-chemical and thermal properties of starch derived from sugar palm tree (Arenga pinnata). *Asian Journal of Chemistry*, 26(4), pp. 955–959.
- Sahari, Japar, Sapuan, S. M., Zainudin, E. S., & Maleque, M. A. (2013). Flexural and Impact Properties of Biopolymer Derived from Sugar Palm Tree. *Advanced Materials Research*, 701, pp. 225–228.
- Salleh, Z., Taib, Y. M., Hyie, K. M., Mihat, M., Berhan, M. N., & Ghani, M. A. A. (2012). Fracture toughness investigation on long kenaf/woven glass hybrid composite due to water absorption effect. *Procedia Engineering*.
- Samariha, A., Bastani, A., Nemati, M., Kiaei, M., Nosrati, H., & Farsi, M. (2013). Investigation of the mechanical properties of bagasse flour/polypropylene composites. *Mechanics of Composite Materials*, 49(4), pp. 447–454.
- Sanjay K. Mazumdar (2002). *Composite Manufacturing Materials, Product and Process Engineering*: CRC Press.
- Sankar, P. H., Reddy, Y. V. M., Reddy, K. H., Kumar, M. A., & Ramesh, A. (2015). The Effect of Fiber Length on Tensile Properties of Polyester Resin Composites Reinforced by the Fibers of *Sansevieria trifasciata*. *International Letters of Natural Sciences*, 8, pp. 7–13.
- Santhosh, J., Balanarasimman, N., Chandrasekar, R., & Raja, S. (2015). Study of Properties of Banana Fiber Reinforced Composites. *International Journal of Research in Engineering and Technology*, 03(11), pp. 144–150.

- Santos, E. F., Mauler, R. S., & Nachtigall, S. M. B. (2009). Effectiveness of maleated- and silanized-PP for coir fiber-filled composites. *Journal of Reinforced Plastics and Composites*, 28(17), pp. 2119–2129.
- Santosh Kumar, D. S., Praveen, B. A., Kiran Aithal, S., & U N, K. (2015). Development of Pineapple Leaf Fiber Reinforced Epoxy Resin Composites. *International Research Journal of Engineering and Technology*, pp. 2395–56.
- Santosha, P. V. C. R. K., Shiva Shankare Gowda, A. S., & Manikanth, V. (2018). Effect of fiber loading on thermal properties of banana and pineapple leaf fiber reinforced polyester composites. *Materials Today: Proceedings*, 5(2), pp. 5631–5635.
- Sanyang, M. L., Sapuan, S. M., Jawaidd, M., Ishak, M. R., & Sahari, J. (2016). Effect of plasticizer type and concentration on physical properties of biodegradable films based on sugar palm (arenga pinnata) starch for food packaging. *Journal of Food Science and Technology*, 53(1), pp. 326–336.
- Sanyang, Muhammed L., Sapuan, S. M., Jawaidd, M., Ishak, M. R., & Sahari, J. (2015). Effect of plasticizer type and concentration on tensile, thermal and barrier properties of biodegradable films based on sugar palm (Arenga pinnata) starch. *Polymers*, 7(6), pp. 1106–1124.
- Sarifuddin, N., Ismail, H., & Ahmad, Z. (2012). Effect of fiber loading on properties of thermoplastic sago starch/kenaf core fiber biocomposites. *BioResources*, 7(3), pp. 4294–4306.
- Satyanarayana, K. G., Arizaga, G. G. C., & Wypych, F. (2009). Biodegradable composites based on lignocellulosic fibers-An overview. In *Progress in Polymer Science (Oxford)*.
- Selamat, M. Z., Kasim, A. N., Shamsudin, S. A., Ahadlin, M., & Daud, M. (2014). Effect Of Bamboo Fibre Length On The Mechanical Properties Of Bamboo Fibre / Polypropylene Composite. *November*, pp. 10–11.
- Selamat, M. Z., Razi, M., Kasim, A. N., Dharmalingam, S., & Putra, A. (2016). Mechanical Properties of Starch Composite Reinforced by Pineapple Leaf Fiber (PLF) from Josapine Cultivar. *11(16)*, pp. 9783–9788.
- Senthilkumar, K., Saba, N., Rajini, N., Chandrasekar, M., Jawaidd, M., Siengchin, S., & Alotman, O. Y. (2018). Mechanical properties evaluation of sisal fibre reinforced polymer composites: A review. In *Construction and Building Materials*.

- Shalwan, A., & Yousif, B. F. (2013). In state of art: Mechanical and tribological behaviour of polymeric composites based on natural fibres. *Materials and Design*.
- Sharath, G. P., Kishor, B. S., Vinod, B., & Naveen, A. (2016). Effect of Fiber Length on the Mechanical Properties of Hybrid Ceasar Weed/Coir Reinforced Polyester Composite. *International Journal of Science Technology & Engineering - IJSTE*, 2(11), pp. 555–559.
- Sheikh Md Fadzullah, S. H., Mustafa, Z., Ramli, S. N. R., Yaacob, Q., & Mohamed Yusoff, A. F. (2016). Preliminary Study on the Mechanical Properties of Continuous Long Pineapple Leaf Fibre Reinforced PLA Biocomposites. *Key Engineering Materials*, 694(i), pp. 18–22.
- Shinoj, S., Visvanathan, R., Panigrahi, S., & Kochubabu, M. (2011). Oil palm fiber (OPF) and its composites: A review. *Industrial Crops and Products*, 33(1), pp. 7–22.
- Shogren, R. L., Lawton, J. W., Doane, W. M., & Tiefenbacher, K. F. (1998). Structure and morphology of baked starch foams. *Polymer*, 39(25), pp. 6649–6655.
- Shyamraj, R., Sivasubramanian, P., & Dhanusha, P. (2013). Investigations on Mechanical Properties of Pineapple Fiber Reinforced Polymer Composite Material. *International Journal of Scientific & Engineering Research*, 4(8), pp. 4–8.
- Singh, M., Vinodh Kumar, S., & Waghmare, S. (2016). Mud Plaster Wall Paintings of Bhaja Caves: Composition and Performance Characteristics. *Indian Journal of History of Science*, 51(3), pp. 431–442.
- Siregar, J. P., Sapuan, S. M., Rahman, M. Z. A., & Zaman, H. M. D. K. (2010). The effect of alkali treatment on the mechanical properties of short pineapple leaf fibre (PALF) reinforced high impact polystyrene (HIPS) composites. *Advanced Composites Letters*, 18(1), pp. 25–29.
- Siregar, J. P., Sapuan, S. M., Rahman, M. Z. A., & Zaman, H. M. D. K. (2012). Effects of alkali treatments on the tensile properties of pineapple leaf fibre reinforced high impact polystyrene composites. *Pertanika Journal of Science and Technology*, 20(2), pp. 409–414.
- Siregar, Januar Parlaungan, Salit, M. S., Ab Rahman, M. Z., & Mohd Dahlan, K. Z. H. (2011). Thermogravimetric analysis (TGA) and differential scanning calometric (DSC) analysis of pineapple leaf fibre (PALF) reinforced high impact

- polystyrene (HIPS) composites. *Pertanika Journal of Science and Technology*, 19(1), pp. 161–170.
- Smithipong, W., Tantatherdtam, R., & Chollakup, R. (2015). Effect of pineapple leaf fiber-reinforced thermoplastic starch/poly (lactic acid) green composite: Mechanical, viscosity, and water resistance properties. *Journal of Thermoplastic Composite Materials*, 28(5), pp. 717–729.
- Sobczak, L., Lang, R. W., & Haider, A. (2012). Polypropylene composites with natural fibers and wood - General mechanical property profiles. *Composites Science and Technology*.
- Sood, M., & Dwivedi, G. (2018). Effect of fiber treatment on flexural properties of natural fiber reinforced composites: A review. *Egyptian Journal of Petroleum*, 27(4), pp. 775–783.
- Sreekala, M. S., George, J., Kumaran, M. G., & Thomas, S. (2002). The mechanical performance of hybrid phenol-formaldehyde-based composites reinforced with glass and oil palm fibres. *Composites Science and Technology*.
- Sreenivasan, V. S., Rajini, N., Alavudeen, A., & Arumugaprabu, V. (2015). Dynamic mechanical and thermo-gravimetric analysis of Sansevieria cylindrica/polyester composite: Effect of fiber length, fiber loading and chemical treatment. *Composites Part B: Engineering*.
- Sri Aprilia, N. A., Abdul Khalil, H. P. S., Bhat, A. H., Dungani, R., & Hossain, M. S. (2014). Exploring material properties of vinyl ester biocomposites filled carbonized Jatropha seed shell. *BioResources*, 9(3), pp. 4888–4898.
- Srinivasa, C. V., & Bharath, K. N. (2015). Effect of Alkali Treatment on Impact Behavior of Areca Fibers Reinforced Polymer Composites Effect of Alkali Treatment on Impact Behavior of Areca Fibers Reinforced Polymer Composites. *JANUARY 2013*, pp. 875–879.
- Stepto, R. F. T. (2003). The Processing of Starch as a Thermoplastic. *Macromolecular Symposia*, 201, pp. 203–212.
- Sumaila, M., Amber, I., & Bawa, M. (2013). Effect of Fiber Length on the Physical and Mechanical Properties of Random Orinted , Nonwoven Short Banana (Musa Balbisiana) Fibre/Epoxy Composite. 2(1), pp. 39–49.

- Suwanruji, P., Tuechart, T., Smitthipong, W., & Chollakup, R. (2017). Modification of pineapple leaf fiber surfaces with silane and isocyanate for reinforcing thermoplastic. *Journal of Thermoplastic Composite Materials*, 30(10), pp. 1344-1360.
- Tajvidi, M., Najafi, S. K., & Moteei, N. (2006). Long-term water uptake behavior of natural fiber/polypropylene composites. *Journal of Applied Polymer Science*, 99(5), pp. 2199–2203.
- Tanase, E. E., Rapa, M., & Popa, O. (2014). Biopolymers Based on Renewable Resources - A Review. *Scientific Bulletin. Series F. Biotechnologies*, 18.
- Taufiq, M. ., Ridzuan, M., & Mustafa, Z. (2018). Characterisation of wood plastic composite manufactured from kenaf fi bre reinforced recycled-unused plastic blend. 189(January), pp. 510–515.
- Teacă, C. A., Bodîrlău, R., & Spiridon, I. (2012). Effect of cellulose reinforcement on the properties of organic acid modified starch microparticles/plasticized starch bio-composite films. *Carbohydrate Polymers*, 93(1), pp. 307–315.
- Teixeira, E. de M., Lotti, C., Correˆa, A. C., Teodoro, K. B. R., Marconcini, J. M., & Mattoso, L. H. C. (2010). Thermoplastic Corn Starch Reinforced with Cotton Cellulose Nanofibers. *Polymers and Polymer Composites*, 21(7), pp. 449–456.
- Teixeira, E. de M., Pasquini, D., Curvelo, A. A. S., Corradini, E., Belgacem, M. N., & Dufresne, A. (2009). Cassava bagasse cellulose nanofibrils reinforced thermoplastic cassava starch. *Carbohydrate Polymers*, 78(3), pp. 422–431.
- Teles, M. C. A., Glória, G. O., Altoé, G. R., Amoy Netto, P., Margem, F. M., Braga, F. O., & Monteiro, S. N. (2015). Evaluation of the Diameter Influence on the Tensile Strength of Pineapple Leaf Fibers (PALF) by Weibull Method. *Materials Research*, 18(suppl 2), pp. 185–192.
- Tester, R. F., Karkalas, J., & Qi, X. (2004). Starch - Composition, fine structure and architecture. *Journal of Cereal Science*, 39(2), pp. 151–165.
- Thakur, V. K., Thakur, M. K., & Gupta, R. K. (2014). Graft copolymers of natural fibers for green composites. *Carbohydrate Polymers*, 104(1), pp. 87–93.
- Thiruchitrambalam, M., Athijayamani, A., Sathiyamurthy, S., & Syed Abu Thaheer, A. (2010). A review on the natural fiber-reinforced polymer composites for the development of roselle fiber-reinforced polyester composite. In *Journal of Natural Fibers*.

- Ticoalu, A., Aravinthan, T., & Cardona, F. (2010). A review of current development in natural fiber composites for structural and infrastructure applications. *Southern Region Engineering Conference 2010, SREC 2010 - Incorporating the 17th Annual International Conference on Mechatronics and Machine Vision in Practice, M2VIP 2010, November*, pp. 1–5.
- Todkar, S. S., & Patil, S. A. (2019). Review on mechanical properties evaluation of pineapple leaf fibre (PALF) reinforced polymer composites. *Composites Part B: Engineering*.
- Tome, L. C., Fernandes, S. C. M., Sadocco, P., Causio, J., Silvestre, A. J. D., Neto, C. P., & Freire, C. S. R. (2012). Antibacterial thermoplastic starch-chitosan based materials prepared by melt-mixing. *BioResources*, 7(3), pp. 3398–3409.
- Tran, T. P. T., Bénézet, J. C., & Bergeret, A. (2014). Rice and Einkorn wheat husks reinforced poly(lactic acid) (PLA) biocomposites: Effects of alkaline and silane surface treatments of husks. *Industrial Crops and Products*, 58, pp. 111–124.
- Valadez-Gonzalez, A., Cervantes-Uc, J. M., Olayo, R., & Herrera-Franco, P. J. (1999). Effect of fiber surface treatment on the fiber-matrix bond strength of natural fiber reinforced composites. *Composites Part B: Engineering*.
- Venkateshappa, S. C., Bennehalli, B., Kenchappa, M. G., & Ranganagowda, R. P. G. (2010). Flexural behaviour of areca fibers composites. *BioResources*, 5(3), pp. 1846–1858.
- Venkateshwaran, N., Elayaperumal, A., & Jagatheeshwaran, M. S. (2011). Effect of fiber length and fiber content on mechanical properties of banana fiber/epoxy composite. *Journal of Reinforced Plastics and Composites*, 30(19), pp. 1621–1627.
- Vijaya Ramnath, B., Junaid Kokan, S., Niranjan Raja, R., Sathyanarayanan, R., Elanchezhian, C., Rajendra Prasad, A., & Manickavasagam, V. M. (2013). Evaluation of mechanical properties of abaca-jute-glass fibre reinforced epoxy composite. *Materials and Design*.
- Vilaseca, F., Mendez, J. A., Pèlach, A., Llop, M., Cañigüeral, N., Gironès, J., Turon, X., & Mutjé, P. (2007). Composite materials derived from biodegradable starch polymer and jute strands. *Process Biochemistry*, 42(3), pp. 329–334.
- Vinod, B., & Sudev, J. L. (2013). Effect of Fiber length on the Tensile Properties of PALF Reinforced Bisphenol Composites. *International Journal of Engineering, Business and Enterprise Applications (IJEBA)*, 2(8), pp. 158–162.

- Vroman, I., & Tighzert, L. (2009). Biodegradable polymers. *Materials*, 2(2), pp. 307–344.
- Wang, B., Panigrahi, S., Tabil, L., & Crerar, W. (2007). Pre-treatment of flax fibers for use in rotationally molded biocomposites. *Journal of Reinforced Plastics and Composites*, 26(5), pp. 447–463.
- Wang, C. Z., Li, F. Y., Wang, L. M., Li, J. F., Guo, A. F., Zhang, C. W., & Liu, P. (2015). Research on thermoplastic starch and different fiber reinforced biomass composites. *RSC Advances*, 5(62), pp. 49824–49830.
- Wang, W., Sain, M., & Cooper, P. A. (2006). Study of moisture absorption in natural fiber plastic composites. *Composites Science and Technology*.
- Wisittanawat, U., Thanawan, S., & Amornsakchai, T. (2014). Mechanical properties of highly aligned short pineapple leaf fiber reinforced - Nitrile rubber composite: Effect of fiber content and Bonding Agent. *Polymer Testing*, 35, pp. 20–27.
- Wu, J., Yu, D., Chan, C. M., Kim, J., & Mai, Y. W. (2000). Effect of Fiber Pretreatment Condition on the Interfacial Strength and Mechanical Properties of Wood Fiber/PP Composites. *Journal of Applied Polymer Science*, 76(7), pp. 1000–1010.
- Xie, F., Pollet, E., Halley, P. J., & Avérous, L. (2013). Starch-based nano-biocomposites. *Progress in Polymer Science*, 38(10–11), pp. 1590–1628.
- Xie, Y., Hill, C. A. S., Xiao, Z., Militz, H., & Mai, C. (2010). Silane coupling agents used for natural fiber/polymer composites: A review. In *Composites Part A: Applied Science and Manufacturing*.
- Xiong, Z., Ma, S., Fan, L., Tang, Z., Zhang, R., Na, H., & Zhu, J. (2014). Surface hydrophobic modification of starch with bio-based epoxy resins to fabricate high-performance polylactide composite materials. *Composites Science and Technology*, 94, pp. 16–22.
- Yahaya, R., Sapuan, S. M., Jawaid, M., Leman, Z., & Zainudin, E. S. (2014). Mechanical performance of woven kenaf-Kevlar hybrid composites. *Journal of Reinforced Plastics and Composites*, 33(24), pp. 2242–2254.
- Yantaboot, K., & Amornsakchai, T. (2017). Effect of mastication time on the low strain properties of short pineapple leaf fiber reinforced natural rubber composites. *Polymer Testing*, 57, pp. 31–37.

- Yu, H., Longana, M. L., Jalalvand, M., Wisnom, M. R., & Potter, K. D. (2015). Pseudo-ductility in intermingled carbon/glass hybrid composites with highly aligned discontinuous fibres. *Composites Part A: Applied Science and Manufacturing*, 73(March), pp. 35–44.
- Yusof, Y., Yahya, S. A., & Adam, A. (2015). Novel Technology for Sustainable Pineapple Leaf Fibers Productions. *Procedia CIRP*, 26, pp. 756–760.
- Zahari, W. Z. W., Badri, R. N. R. L., Ardyananta, H., Kurniawan, D., & Nor, F. M. (2015). Mechanical Properties and Water Absorption Behavior of Polypropylene / Ijuk Fiber Composite by Using Silane Treatment. *Procedia Manufacturing*, 2(February), pp. 573–578.
- Zainuddin, S. Y. Z., Ahmad, I., Kargarzadeh, H., Abdullah, I., & Dufresne, A. (2013). Potential of using multiscale kenaf fibers as reinforcing filler in cassava starch-kenaf biocomposites. *Carbohydrate Polymers*, 92(2), pp. 2299–2305.
- Zhang, S. D., Zhang, Y. R., Zhu, J., Wang, X. L., Yang, K. K., & Wang, Y. Z. (2007). Modified corn starches with improved comprehensive properties for preparing thermoplastics. *Starch/Staerke*, 59(6), pp. 258–268.
- Zhang, Y., Rempel, C., & Liu, Q. (2014). Thermoplastic Starch Processing and Characteristics-A Review. *Critical Reviews in Food Science and Nutrition*, 54(10), pp. 1353–1370.
- Zhang, Z., & Zhu, S. (2000). Microvoids in unsaturated polyester resins containing poly(vinyl acetate) and composites with calcium carbonate and glass fibers. *Polymer*.
- Zou, W., Yu, L., Liu, X., Chen, L., Zhang, X., Qiao, D., & Zhang, R. (2012). Effects of amylose/amylopectin ratio on starch-based superabsorbent polymers. *Carbohydrate Polymers*, 87(2), pp. 1583–1588.
- Zuhri, M., Yusoff, M., Mohd Sapuan, S., Ismail, N., & Wirawan, R. (2010). Mechanical properties of short random oil palm fibre reinforced epoxy composites. *Sains Malaysiana*, 39(1), pp. 87–92.